



This project utilises Dynamic finish to create the appearance of natural hewn stone.



Construction Notes

- There are 12.5 blocks in every square metre of wall surface area.
- 1m³ of mortar is required for approximately 800 blocks.
- For a 1:1:6 mortar mix, the approximate quantities required for 1m³ of mortar are:
 - 6 bags of cement
 - 6 bags of lime
 - 1.2m³ of damp sand
- Blocks should be kept dry and away from moisture prior to installation.

- It is essential that mortar smears be removed before mortar sets as acid cleaning at a later stage may affect colour integrity.
- All products have been tested to comply with AS/NZS 4455-1997. Designers should consult the Australian Standard for Masonry Structures, AS 3700-2001, and if necessary seek advice from a registered professional when designing concrete masonry structures.

Technical Information

- Colours and textures shown in this brochure are indicative only. Some variations may occur during the manufacturing process. Please obtain a current batch sample before making a final decision.
- Lead times may apply to premium masonry products. Please contact your Austral Masonry representative for more information.



Rochedale: 105 Gardner Rd, Rochedale (07) 3347 2111 | **Riverview:** 103 Riverview Rd, Riverview (07) 3816 2934 | **Gold Coast:** 3 Central Dr, Burleigh (07) 5593 5955
Toowoomba: 29 Mort St, Toowoomba (07) 4632 6377 | **Sunshine Coast:** Cnr Erang St & Nicklin Way, Currimundi (07) 5493 7441 | **Caloundra:** 14 Daniel St, Caloundra (07) 5491 2933
Gympie: Cnr Bruce Hwy & Woondum Rd, Gympie (07) 5483 5144 | **Proserpine:** Bruce Hwy, Proserpine (07) 4945 1877 | **Ayr:** 7 Cornford Cres, Ayr (07) 4783 2966
Townsville: Lot 2 Blakey St, Garbutt (07) 4775 6944 | **Silkwood:** Bruce Hwy, Silkwood (07) 4065 2233 | **Cairns:** 76 Swallow Rd, Edmonton (07) 4045 5309

Website: www.australmasonry.com.au
Email: designinfo@australmasonry.com.au

Product samples are available. Austral Masonry provide a single outside face finish, the manufacturing process causes unavoidable imperfections on the smooth inside face of blocks. Photographs should be considered indicative of colour and texture only. April 2008. Austral Masonry ABN 30 000 646 695.



