


## Product Details

Product Range	Architec Split Face
Texture Finish	Split Face
Colours	Pearl Grey, Alabaster, Almond & Charcoal
Product Code	
Format	30.142 Recessed Web
Place of Manufacture	Oakdale, New South Wales
Length (mm)	390
Width (mm)	290
Height (mm)	190
Size	390x290x190
Core Volume (%)	-
Characteristic Unconfined Compressive Strength (f'uc) MPa	>15
Minimum Shell Thickness (mm)	-
Weight	21.3
Units Per Tonne	46.948356807512
Units Per Pallet	60
Units per Square Metre	-
Durability Class	Exposure Grade
Slip Resistance	
Wall Mass Inc Hollow	-
Solar Absorption Rating	0.69
LRV	-
FRL	-
EPD	Yes
Declare	No
Recycled Content %	no

## Diagram



## Fire Resistance Levels^

Structural Adequacy	60 to 240
Integrity	Hollow: 60. Core Filled: 240.
Insulation	Hollow: 60. Core Filled: 240.


## Notes

This data represents average results from production lots based on the results achieved by samples selected at random for testing. Figures are accurate at date of publication and subject to change without notice. Contact Austral Masonry for confirmation of product specification

## Product Details

Product Range	Architec Split Face
Texture Finish	Split Face
Colours	Alabaster, Pearl Grey, Almond & Charcoal
Product Code	
Format	20.139 Corner Block
Place of Manufacture	Oakdale, New South Wales
Length (mm)	390
Width (mm)	190
Height (mm)	190
Size	390x190x190
Core Volume (%)	-
Characteristic Unconfined Compressive Strength (f'uc) MPa	>15
Minimum Shell Thickness (mm)	30
Weight	20
Units Per Tonne	50
Units Per Pallet	90
Units per Square Metre	-
Durability Class	Exposure Grade
Slip Resistance	
Wall Mass Inc Hollow	-
Solar Absorption Rating	0.48
LRV	-
FRL	-
EPD	Yes
Declare	No
Recycled Content %	no

## Diagram



## Fire Resistance Levels^

Structural Adequacy	60 to 240
Integrity	Hollow: 60
Insulation	Hollow: 60


## Notes

Maximum slenderness ratio (srf) from AS3700:2018 Table 6.1 is: 18.0 at 60 minutes | 17.0 at 90 minutes | 16.0 at 120 minutes | 15.5 at 180 minutes | 15.5 at 240 minutes. This data represents average results from production lots based on the results achieved by samples selected at random for testing. Figures are accurate at date of publication and subject to change without notice. Contact us for confirmation of product specification. Tested as per AS/NZS 4455.1: 2008 and 4456: 2003. Fire resistance levels as per AS3700: 2018. Acoustic opinion derived from Day Design Pty Ltd. 2012. Tested in accordance with AS 1191:1001 and AS/NZS 1276.1:1999.

## Product Details

Product Range	Architec Split Face
Texture Finish	Split Face
Colours	Pearl Grey, Charcoal, Alabaster & Almond
Product Code	
Format	20.142 Recessed Web
Place of Manufacture	Oakdale, New South Wales
Length (mm)	390
Width (mm)	190
Height (mm)	190
Size	390x190x190
Core Volume (%)	-
Characteristic Unconfined Compressive Strength (f'uc) MPa	>15
Minimum Shell Thickness (mm)	30
Weight	18.2
Units Per Tonne	54.945054945055
Units Per Pallet	90
Units per Square Metre	-
Durability Class	Exposure Grade
Slip Resistance	
Wall Mass Inc Hollow	-
Solar Absorption Rating	0.69
LRV	-
FRL	-
EPD	Yes
Declare	No
Recycled Content %	no

## Diagram



## Fire Resistance Levels^

Structural Adequacy	60 to 240
Integrity	Hollow: 60. Core Filled: 240.
Insulation	Hollow: 60. Core Filled: 240.


## Notes

Maximum slenderness ratio (srf) from AS3700:2018 Table 6.1 is: 18.0 at 60 minutes | 17.0 at 90 minutes | 16.0 at 120 minutes | 15.5 at 180 minutes | 15.5 at 240 minutes. This data represents average results from production lots based on the results achieved by samples selected at random for testing. Figures are accurate at date of publication and subject to change without notice. Contact us for confirmation of product specification. Tested as per AS/NZS 4455.1: 2008 and 4456: 2003. Fire resistance levels as per AS3700: 2018. Acoustic opinion derived from Day Design Pty Ltd. 2012. Tested in accordance with AS 1191:1001 and AS/NZS 1276.1:1999.

## Product Details

Product Range	Architec Split Face
Texture Finish	Split Face
Colours	Alabaster, Almond, Pearl Grey & Charcoal
Product Code	
Format	30.121 Full
Place of Manufacture	Oakdale, New South Wales
Length (mm)	390
Width (mm)	290
Height (mm)	190
Size	390x290x190
Core Volume (%)	-
Characteristic Unconfined Compressive Strength (f'uc) MPa	>15
Minimum Shell Thickness (mm)	-
Weight	21.3
Units Per Tonne	46.948356807512
Units Per Pallet	60
Units per Square Metre	-
Durability Class	Exposure Grade
Slip Resistance	
Wall Mass Inc Hollow	-
Solar Absorption Rating	0.48
LRV	-
FRL	-
EPD	Yes
Declare	No
Recycled Content %	no

## Diagram



## Fire Resistance Levels^

Structural Adequacy	60 to 240
Integrity	Hollow: 60. Core Filled: 240.
Insulation	Hollow: 60. Core Filled: 240.


## Notes

This data represents average results from production lots based on the results achieved by samples selected at random for testing. Figures are accurate at date of publication and subject to change without notice. Contact Austral Masonry for confirmation of product specification

## Product Details

Product Range	Architec Split Face
Texture Finish	Split Face
Colours	Charcoal, Alabaster, Pearl Grey & Almond
Product Code	
Format	20.121 Full
Place of Manufacture	Oakdale, New South Wales
Length (mm)	390
Width (mm)	190
Height (mm)	190
Size	390x190x190
Core Volume (%)	-
Characteristic Unconfined Compressive Strength (f'uc) MPa	>15
Minimum Shell Thickness (mm)	30
Weight	17.7
Units Per Tonne	56.497175141243
Units Per Pallet	90
Units per Square Metre	-
Durability Class	Exposure Grade
Slip Resistance	
Wall Mass Inc Hollow	230
Solar Absorption Rating	0.87
LRV	-
FRL	-
EPD	Yes
Declare	No
Recycled Content %	no

## Diagram



## Fire Resistance Levels^

Structural Adequacy	60 to 240
Integrity	Hollow: 60
Insulation	Hollow: 60


## Notes

Maximum slenderness ratio (srf) from AS3700:2018 Table 6.1 is: 18.0 at 60 minutes | 17.0 at 90 minutes | 16.0 at 120 minutes | 15.5 at 180 minutes | 15.5 at 240 minutes. This data represents average results from production lots based on the results achieved by samples selected at random for testing. Figures are accurate at date of publication and subject to change without notice. Contact us for confirmation of product specification. Tested as per AS/NZS 4455.1: 2008 and 4456: 2003. Fire resistance levels as per AS3700: 2018. Acoustic opinion derived from Day Design Pty Ltd. 2012. Tested in accordance with AS 1191:1001 and AS/NZS 1276.1:1999.

## Product Details

Product Range	Architec Split Face
Texture Finish	Split Face
Colours	Charcoal, Pearl Grey, Almond & Alabaster
Product Code	
Format	10.109 Full
Place of Manufacture	Oakdale, New South Wales
Length (mm)	390
Width (mm)	90
Height (mm)	90
Size	390x90x90
Core Volume (%)	-
Characteristic Unconfined Compressive Strength (f'uc) MPa	>10
Minimum Shell Thickness (mm)	-
Weight	7.2
Units Per Tonne	138.88888888889
Units Per Pallet	288
Units per Square Metre	-
Durability Class	Exposure Grade
Slip Resistance	
Wall Mass Inc Hollow	200
Solar Absorption Rating	-
LRV	-
FRL	-
EPD	Yes
Declare	No
Recycled Content %	no

## Diagram



## Fire Resistance Levels^

Structural Adequacy	60 to 240
Integrity	Hollow: 60
Insulation	Hollow: 60

## Notes

Maximum slenderness ratio (srf) from AS3700:2018 Table 6.1 is: 18.0 at 60 minutes | 17.0 at 90 minutes | 16.0 at 120 minutes | 15.5 at 180 minutes | 15.5 at 240 minutes. This data represents average results from production lots based on the results achieved by samples selected at random for testing. Figures are accurate at date of publication and subject to change without notice. Contact us for confirmation of product specification. Tested as per AS/NZS 4455.1: 2008 and 4456: 2003. Fire resistance levels as per AS3700: 2018. Acoustic opinion derived from Day Design Pty Ltd. 2012. Tested in accordance with AS 1191:1001 and AS/NZS 1276.1:1999.